

Description

Clysar® EVOX™ shrink film is a versatile, high-performance recyclable polyolefin shrink film developed to meet consumer demand for sustainability in branded retail packaging. Prequalified for Store Drop-Off label use with an official letter of prequalification, this market-leading film is ultra-strong, sparkling clear and exceptionally tough. It runs flawlessly at high speeds, on a variety of equipment, with wide

Clysar® EVOX™ Films

DATA SHEET

Uses

Clysar® EVOX™ shrink film is a high-performance drop-in solution for brands seeking a sustainable alternative that meets recyclable labeling initiatives, delivers a premium package appearance and provides outstanding product bundling and protection.

A highly functional alternative for non-recyclable crosslinked films, Clysar® EVOX™ film packages virtually any type of product and offers superior toughness and seal strength, optics and cleanup.



High-Speed,
Recyclable Film for
Ultimate Protection

Significant Features

General

- Meets consumer demand for recyclable packaging: designed for recovery/recyclability at drop-off points nationwide.
- Prequalified by How2Recycle® for Store Drop-off recycling.
- Excellent toughness and tear resistance.
- High gloss, clarity and shine.
- Great package cleanup and appearance.
- Ideal for printed shrink film applications, heavy multi-packs and more.

Equipment

- Designed for high-speed applications.
- Performs on multiple types of packaging equipment including manual, semi-automatic, automatic and static seal machines.

Sealing

- Provides strong, durable seals with all sealing systems including wires, knives and electrostatic overlap.
- Exceptionally wide sealing window.
- Requires little or no cooling dwell for faster throughput.

Shrinking

- Exceptional heat/burn-through resistance.
- Higher than typical shrink force for robust, tight, finished packages.
- Ideal for bundling, multi-packs and shipping stabilization.

Recyclability

Clysar® EVOX™ shrink film is prequalified for the Store Drop-off label by How2Recycle, and has obtained an official letter of prequalification.



Recyclable
Shrink Film

Prequalified for the Store Drop-Off Label,
with official letter of prequalification
from the How2Recycle® Program



how2recycle.info

operating windows.

How2Recycle is the only label program that can supply the official **How2Recycle** icon for packaging. In order to use the Store Drop-Off label on your EVOX™ shrink package, you will need to contact **How2Recycle** directly and complete the **How2Recycle** label request form. If you have any questions regarding the information necessary to complete the label request, please contact your Clysar representative for assistance.

Clysar, LLC

888-4-CLYSAR
marketing@clysar.com

Highway 67 South
Clinton, IA 52732

www.clysar.com

Clysar®

FDA/USDA Status

Clysar® films sold by Clysar, LLC, for food packaging use comply with U.S. Food and Drug Administration (FDA) requirements under the Federal Food, Drug and Cosmetic Act as amended. Clysar complies with FDA regulation 21 CFR 177.1520—Olefin polymers, allowing use for articles that contact food, except for articles used for packing or holding food during cooking.

Use

Clysar, LLC, does not recommend using traditional heating or cooking methods for foods wrapped in Clysar® shrink films. For conditions specific to microwave cooking, please request documentation that is specific for your application through your Clysar representative.

Disposal

Preferred options for disposal are: (1) Store drop-off recycling and (2) incineration with energy recovery.

Storage

Storage below 32°C (90°F) is recommended. Prolonged exposure to temperatures moderately above 32°C (90°F) or brief exposure to temperatures well above 32°C (90°F) may cause difficulty in unwinding film.

For more detailed information on the safe handling of Clysar® films, a "Safety in Handling and Use" guide or the OSHA Material Safety Data Sheets can be obtained from your Clysar representative.

Standard Put-Ups

- Available gauges: 45, 55 and 70
- Flat film is available in custom widths from 5" to 56" increments.*
- Folded film is available in custom widths from 5" to 37" in 1" increments.*
- Folded film will have half the linear footage of flat film for same gauge and roll dimensions.
- Pre-perforated film in standard pattern is available for all gauges for folded and flat film.
- EVOX™ film is wound on 3" and 6" cores to the standard roll sizes shown in Table 1.

*Contact your Clysar representative for width-specific information.

Summary of Properties

Clysar® EVOX™ - Linear Footage Flat Film (Table 1)

Core I.D., in.	Roll O.D., in.	Gauge		
		45	55	70
3	9½	11,660	9,540	7,500
3	13	23,320	19,080	15,000
6	11	11,660	9,540	7,500
6	14	23,320	19,080	15,000
6	18¾	46,640	38,160	30,000

Typical Properties of Clysar® EVOX™ Film (Table 2)

Property	ASTM Test Method	Unit	Gauge		
			45	55	70
Haze (avg)	D1003	%	2.5	2.7	3.0
Gloss at 20° (min)	D2457	-	143	148	148
COF, Kinetic	D1894	-	0.23	0.24	0.20
Shrinkage, 90°C Hot Water Bath	D2732-14	% (area)	50	50	50
Shrink Force, 100°C (212°F)	D2838	g	65	70	75
Stiffness Modulus (avg)	D882	kpsi	66	65	64
Tensile Strength (avg)	D882	kpsi	15	15	15
Elongation (avg)	D882	%	126	129	140
Tear Strength (avg) (Elmendorf)	D1922	g	11	17	20
Spencer Impact	D3420	lbf	6.40	9.00	13.00
WVTR	F1249	g/100 in ² /24 hr	1.7	1.5	1.4
Oxygen Transmission	D3985	cc/100 in ² /24 hr	850	550	500

Note: These values are typical data for EVOX™ shrink film and are not intended for use as limiting specifications.

Clysar®

888-4-CLYSAR
marketing@clysar.com
www.clysar.com

The technical data contained herein are guides to the use of Clysar® films. The advice contained herein is based upon tests and information believed to be reliable, but users should not rely upon it absolutely for specific applications because performance properties will vary with processing conditions. It is given and accepted at user's risk, and confirmation of its validity and suitability in particular cases should be obtained independently. Clysar makes no guarantees of results and assumes no obligations or liability in connection with its advice. This publication is not to be taken as a license to operate under, or recommendation to infringe, any patents.

CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see Clysar Medical Caution Statement, MCS_02.